

SOUTHWESTERN LABORATORIES

222 Cavalcade Street, 77009-3213
 P.O. Box 8768, Houston, Texas 77249-8768
 Tel (713) 692-9151 Fax (713) 696-6307

Attention: **CARL BODDIE**
INDUSTRIAL POLYMERS CORP.
 3250 SOUTH SAM HOUSON PARKWAY, EAST
 Houston, TX 77047
 (713) 943-8451, 713/943-1525

W/O. No.: IND178-06-15-14854
 Date: 6/25/2001
 P.O. No.: Carl Boddie
 Rev. 1 7/10/2001**

Project: Testing of Urethane Elastomer

PROJECT INFORMATION

Material: Ten (10) Precut Specimens of Urethane Speedliner 1000**
Identification: Specimen Speedliner 1000, #1 thru #5 for tensile testing
 Specimen Speedliner 1000, #1 thru #5 for tear testing
Date Received: 6/15/2001 *Technician :* M. Hendricks
Specification: Per Client, See Table Below *Date of Test:* 6/18/2001
Test Equipment: Instron 4507, S/N H1963 *Procedure:* ASTM D412 & D624

Tensile Test D412

Specimen ID	Tensile Test (psi)	Elongation (%)
1	5556	599
2	6658	596
3	4713	577
4	3927	500
5	2645	578
Average	4700	570

Tear Test D624

Specimen ID	Tear Resistance (lbs/in.)
1	871
2	940
3	867
4	876
5	769
Average	865

NOTE: The submitted material will be discarded after a period of 30 days unless otherwise directed.

SOUTHWESTERN LABORATORIES

