KEVLAR®
only by DuPont

Represented by:
H.M. Royal, Inc. *H.M. Royal of California*
(800) 257-9452 *(800) 826-8175*
www.hmroyal.com

Kevlar® Quality Assurance
Spruance Plant
P.O. Box 27001
Richmond, VA 23261
U.S.A.
Tel. (804)383-3773
Fax. (804)383-3163

PRODUCT SPECIFICATION

Product: **KEVLAR® brand pulp** *Merge:* **1F543**

Type: **953**

Date Effective: **1 November, 2000** *Unit Package:* **Bale**

PROPERTY	***SPECIFICATION***			***TEST METHOD***	
	Nominal	**Low**	**High**	**DuPont**	**TAPPI**
Canadian Standard Freeness, [ML]	140	85	195	TM0772	T-227
Fiber Length, [mm] (1)				TM0534	T-271
- Weighted Average	1.05	0.81	1.29		
Moisture, [%]	6.5	5.0	8.0	TM0893	T-210
Bale Weight, [kg]	4.0	3.9	4.3		

NOTES:

Customers are billed for the commercial weight (oven dry X 1.07) which accounts for 7% moisture regain from specified dry weight (Reference ASTM D1909).

FOOTNOTES:

(1) Measured by FiberExpert.

W.R. Globig
Quality Assurance

ISO 9001:2000 certified.

KEVLAR® is a registered trademark of E. I. du Pont de Nemours and Company an aramid product