

PRIMER SERIES	Physical Properties - Cured				Typical properties - Liquid								
	APPLY	TENSILE STRENGTH ASTM D 412	ELONGATION ASTM D412	TEAR STRENGTH ASTM D 624	USES	COMPONENT A*B*MIXED	VISCOSITY (CPS)	SPECIFIC GRAVITY	HAZARD	COMPONENT BY VOLUME	A*B MIXING BY WEIGHT	WORK LIFE	CURE TIME
PRIMER 450	SPRAY	N/A	N/A	N/A	COATED METAL	7.74 LB	30 CPS	0.93	HAZARD	1A-1B	100A-92B	2 HR@ 72F	24 HOURS @ 72F
PRIMER 460 SPX	SPRAY	N/A	N/A	N/A	FIBER GLASS	7.74 LB	30 CPS	0.93	HAZARD	1A-1B	100A-92B	1 HR @ 72F	24 HOURS @ 72F

\*Cure time depends on temperate and relative humidity