


Industrial Polymers Inc.
 3250 South Sam Houston Parkway East
 Houston, Tx 77047

Test Type
 Tear ASTM D 624

SL-1000 lot # A- 09/06/18 B- 09/07/18

| | |
|----------------------|------------------|
| Vulcanization date | |
| Rate 1 | 500. mm/min |
| Sample Size | 5. |
| Grain direction | Parallel |
| Type of grips | Instron 2713-004 |
| Type testing machine | Instron 3345 |
| Conditioning time | 18 hr @185 F |
| Temperature (F) | 72.0 |
| Humidity (%) | 50.0 |
| Specimen Note | |
| Technician | Chino |

Specimen 1 to 6



Test Results

| | Maximum Load (lbf) | Max Load/Thickness (lb/in) | Specimen Type | Thickness (in) |
|--------------------|--------------------|----------------------------|---------------|----------------|
| 1 | 65.24359 | 981.11 | C | 0.0665 |
| 2 | 57.98779 | 1008.48 | C | 0.0575 |
| 3 | 57.53595 | 951.01 | C | 0.0605 |
| 4 | 58.34323 | 911.61 | C | 0.0640 |
| 6 | 52.14454 | 1002.78 | C | 0.0520 |
| Mean | 58.25102 | 971.00 | | 0.0601 |
| Standard Deviation | 4.65764 | 40.13605 | | 0.00567 |