

TOP COAT SERIES	Physical Properties - Cured					Typical properties - Liquid							
	HARDNESS ASTM D2240	TENSILE ASTM D 412	ELONGATION ASTM D 412	TEAR STRENGTH D 624	COLOR	COMPONENT A*B*MIXED	VISCOSITY (CPS)	SPECIFIC GRAVITY	HAZARD	COMPONENT BY VOLUME	A*B MIXING BY WEIGHT	WORK LIFE	CURE TIME
TOPCOAT #6	70 SHORE A	4252 PSI	165%	1103 LB/IN	CLEAR	7.97 LBS	389 CPS	0.96	HAZARD	1A-1B	100A-90.62B	1 - 1.5 HOURS @ 72F	24 HRS @ 72F
TOPCOAT CRX	75 - 85 SHORE A	2578 PSI	430%	595 LB/IN	CLEAR	7.67 LBS	1340 CPS	0.92	HAZARD	100A-33B	100A-34B	45 MINUTES @ 72F	24 HRS @ 72F

*Cure time depends on temperate and relative humidity